



DuPont™ Teflon® AF

AMORPHOUS FLUOROPOLYMERS

Product Information

General Description

Teflon® AF is a family of amorphous fluoropolymers. These materials are similar to other amorphous polymers in optical clarity and mechanical properties, including strength. They also resemble fluoropolymers in their performance over a wide range of temperatures, outstanding electrical properties, and chemical resistance. They are distinct from other fluoropolymers in that they are soluble in selected solvents and have high gas permeability, high compressibility, high creep resistance, and low thermal conductivity. They have the lowest dielectric constant of any known fluoropolymer.

Processing

Teflon® AF can be compression molded, injection molded, or extruded. Through these processes, various solid shapes can be formed using the product. Forms include rods, tubes, bars, and sheet of various thicknesses.

In addition, Teflon® AF can be dissolved in certain per-fluorinated solvents for the production of highly uniform thin films and coatings. Methods used to produce such forms include spin, spray, and dip coating.

Typical molding temperatures for Teflon® AF 1600 range from 240 to 275°C (464 to 527°F); for Teflon® AF 2400, the range is 340 to 360°C (644 to 680°F). The polymer begins to decompose above 360°C (680°F), so processing above that temperature should be avoided. Corrosion-resistant tooling is recommended, as it is for Teflon® FEP and PFA fluoropolymer resins.

Electrical Applications

In electronics, Teflon® AF may be used in optoelectronic devices where its optical clarity, temperature resistance, and dielectric properties are beneficial. It is essentially transparent to microwaves and can function as a “window” for high frequency antennas. The low dielectric constant and dissipation factor may be advantageous in the construction of electronic devices, including special circuit boards and hybrid devices.

Some specific uses are:

- Teflon® AF has the ability to be cast from solution into a thin film that is transparent and stable to very short wavelength radiation (deep UV). This makes it an excellent candidate for use in pellicles. It has superior electrical properties, particularly for low signal distortion at high frequencies.
- Chemically resistant coating—where its low dielectric constant and low electrical absorption coefficient are important.
- Its moldability plus its low thermal expansion coefficient make it an excellent candidate for connectors.
- It can also be used as a sight window in harsh chemical environments.



The miracles of science™

Optical Applications

Teflon® AF can be used as a low-refractive index coating or covering for optical devices, including those that must operate over a wide temperature range and in chemically aggressive environments. Teflon® AF offers a high level of transmission throughout the optical spectrum from infrared through ultraviolet.

Some specific uses are:

- In fiber optics as a low refractive index, high temperature cladding material over silica, methacrylates, and polycarbonates.
- Its optical properties of high transmission and broad spectrum transmission make it practical as an anti-reflective coating for high energy laser applications.
- The properties of high temperature tolerance, chemical resistance, high transmission, and mechanical strength make the material ideal for use as a window. It would also be good for optical sensing and diagnostic devices.
- The low refractive index combined with its other optical properties make Teflon® AF useful as an antireflective coating. It is also good as a protective coating where optical transmission is important.

Mechanical Applications

Teflon® AF exhibits excellent mechanical and physical properties at end-use temperatures up to the glass transition temperature. Teflon® AF also demonstrates good dimensional stability, reduced mold shrinkage, a smooth surface, and rigidity at high use temperatures. These characteristics, coupled with machinability and processing versatility, make Teflon® AF an excellent candidate for specialized chemical and industrial applications.

Some specific uses are:

- For chemically resistant molded parts and objects
- Sight windows in harsh chemical environments
- Connectors

Chemical Applications

As a fluoropolymer, Teflon® AF has high resistance to chemical attack. Teflon® AF can be fabricated into films, coatings, and smooth surfaced products and also molded into high performance mechanical parts that can function in severe exposure conditions of high temperature, harsh chemicals, and destructive environmental agents. Teflon® AF is an excellent candidate for the demanding and stringent conditions that exist in the electronic, chemical, military, and aerospace industries.

Some specific uses are:

- As a protective coating—where chemical resistance as well as the ability to withstand high temperatures is important: pipes and fittings; conveyor belts; sheets that are in contact with chemicals.
- Chemical containers (for specialty applications)—where it is necessary that the container not react with the contents and optical transmission is important: stopper coatings; bottles (can be shaped).
- Process windows—where the optical properties as well as the chemical inertness are important.
- Membranes and/or separators—the high gas permeability and chemical inertness make it an ideal candidate.
- Its low surface energy makes a good release surface.
- Its high gas permeability makes it an excellent separation medium for gases and liquids.

Safety Precautions

WARNING!

VAPORS CAN BE LIBERATED WHICH MAY BE HAZARDOUS IF INHALED.

Before using Teflon® AF, read the Material Safety Data Sheet and the detailed information in the "Guide to the Safe Handling of Fluoropolymer Resins", latest edition, published by the Fluoropolymers Division of The Society of the Plastics Industry; copies may be obtained from your DuPont representative.

Handling Practices

Teflon® AF resins contain parts per million of residual hexafluoroacetone (HFA). Because HFA hydrates are readily absorbed through the skin, it is necessary to avoid skin contact with the resin during processing. DuPont recommends the use of protective gloves when handling resin during manufacturing operations. Residual gases (including HF, COF₂, CO, and HFA) that may be harmful diffuse from Teflon® AF resins even at room temperature. To avoid exposure, all resin containers should be opened and used only in well ventilated areas using local exhaust ventilation (LEV).

Typical Property Data for Teflon® AF Amorphous Fluoropolymers

Property	ASTM Method	Unit	Grade	
			1600	2400
Electrical				
Dielectric Constant	D150		1.93	1.90
Dissipation Factor	D150		0.0001–0.0002	0.0001–0.0003
Dielectric Strength	D149	kV/0.1 mm	2.1	1.9
Optical				
Optical Transmission	D1003	%	>95	>95
Refractive Index	D542		1.31	1.29
ABBE Number			92	113
Mechanical				
Yield Strength		MPa 23°C (73°F) 150°C (302°F) 220°C (428°F)	27.4 ± 1.0 6.7 ± 5.9	26.4 ± 1.9 8.7 ± 4.0
Tensile Strength	D638	MPa 23°C (73°F) 150°C (302°F) 220°C (428°F)	26.9 ± 1.5 7.7 ± 6.1	26.4 ± 1.9 4.2 ± 1.8
Elongation at Break	D638	% 23°C (73°F) 150°C (302°F) 220°C (428°F)	17.1 ± 5.0 89.3 ± 13.1	7.9 ± 2.3 8.4 ± 4.1
Tensile Modulus	D638	GPa	1.6	1.5
Flexural Modulus	D790	GPa 23°C (73°F) 150°C (302°F) 220°C (428°F)	1.8 ± 0.1 1.0 ± 0.1	1.6 ± 0.1 0.7 ± 0.1
Hardness Rockwell Durometer	D785 D1706	23°C (73°F) Shore D 23°C (73°F) 150°C (302°F) 220°C (428°F)	103 77 70	97.5 75 65
Impact Strength	Notched Izod	N	---	---
Deflection Temperature (66 psi) (264 psi)	D648	°C (°F)	156 (313) 154 (309)	200 (392) 174 (345)
Chemical				
Contact Angle with Water		Degrees	104	105
Critical Surface Energy		Dynes/cm	15.7	15.6
Taber Abrasion		cc/2000 cycles	0.107	0.2
Chemical Resistance				
Water Absorption	D570	%	<0.01	<0.01
Gas Permeability				
H ₂ O		Barrer	1142	4026
O ₂		Barrer	340	990
N ₂		Barrer	130	490
CO ₂		Barrer		2800
Other				
T _g	D3418	°C (°F)	160 (320) ± 5	240 (464) ± 10
Specific Gravity	D792		1.78	1.67
Melt Viscosity	D3835	Pa s	2657 at 250°C, 100s ⁻¹	540 at 350°C, 100s ⁻¹
Volume Coefficient of Thermal Expansion	E831	ppm/°C	260	301

For more information on call (302) 479-7731.

www.teflon.com

DuPont Fluoroproducts
P.O. Box 80713
Wilmington, DE 19880-0713

Europe

DuPont de Nemours Int'l SA
DuPont Fluoroproducts
2, chemin du Pavillon
P.O. Box 50
CH-1218 Le Grand-Saconnex
Geneva, Switzerland
(022) 717511

Japan

DuPont Mitsui Fluorochemicals
Co., Ltd.
Chiyoda Honsha Building
5-18, Sarugaku-cho 1-chome
Chiyoda-ku, Tokyo 101 Japan
81-3-5281-5872

Asia Pacific

DuPont China Holding Co. Ltd.
Bldg. 11, 399 Keyuan Road
Zhangjiang Hi-Tech Park
Pudong New District
Shanghai, 201203, China
Tel: +86 400 88 51 888

Canada

DuPont Canada, Inc.
DuPont Fluoroproducts
P.O. Box 2200, Streetsville
7070 Mississauga Road
Mississauga, Ontario, Canada
L5M 2H3
(800) 207-0756

South America

DuPont do Brasil S/A
Fluoropolymers
Alameda Itapecuru, 506
06454-080 - Alphaville
P.O. Box 263
Barueri, Sao Paulo, Brazil
0800-171715
Produtos.Brazil@bra.dupont.com

Copyright © 2010 DuPont or its affiliates. All rights reserved. The DuPont Oval Logo, DuPont™, The miracles of science™, and Teflon®, are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

CAUTION: Do not use in medical applications involving permanent implantation in the human body or contact with internal body fluids or tissues. For other medical applications, see "DuPont Medical Caution Statement," H-50102.

